



Suwannee American Cement Branford Plant

Portland Cement Type I-II (MH)

Silos: 2, 5

Production Period : 2/1/2020 To 2/29/2020

STANDARD REQUIREMENTS

Chemical Data			Physical Data		
Item	Spec. Limit	Results	Item	Spec. Limit	Results
SiO ₂ (%)	A	20.1	Air Content of mortar (volume %)	12 max	5
Al ₂ O ₃ (%)	6.0 max	5.1	Blaine fineness (m ² /kg)**	260 min / 430 max	402
Fe ₂ O ₃ (%)	6.0 max	3.3	Autoclave expansion (%)	0.80 max	0.06
CaO (%)	A	64.3			
MgO (%)	6.0 max	0.7	Compressive strength (MPa/[psi]):		
SO ₃ (%)*	3.0 max	3.1	1 day		15.8 [2280]
Loss of ignition (%)	3.5 max	3.0	3 days	12.0[1740] min	27.8 [4030]
Na ₂ O (%)	A	0.14	7 days	19.0[2760] min	36.3 [5270]
K ₂ O (%)	A	0.22	28 days (previous month)	28.0[4060] min	45.8 [6640]
Insoluble residue (%)	1.5 max	0.34	Time of setting (minutes)		
CO ₂ (%)	A	1.7	(Vicat) Initial	45 min	100
Limestone (%)	5.0 max	4.4	(Vicat) Final	375 max	235
CaCO ₃ in limestone (%)	70 min	88			
Inorganic process addition (%)	5.0 max	--	Heat of hydration (ASTM C1702 3d) (J/g)	B	286
Sum of C ₃ S + 4.75C ₃ A	100 max	92	Mortar Bar Expansion (ASTM C1038) (%)*	0.020 max	0.006
Potential phase composition			Base Cement Phase Composition		
C ₃ S (%)	A	55	C ₃ S (%)		57
C ₂ S (%)	A	15	C ₂ S (%)		16
C ₃ A (%)	8 max	8	C ₃ A (%)		8
C ₄ AF (%)	A	10	C ₄ AF (%)		10

OPTIONAL REQUIREMENTS

Item	Spec. Limit	Results	Item	Spec. Limit	Results
Equiv. Alkalies (%)	0.60 max	0.29	False Set (%)	50 min	87
Chloride (%)	B	0.01	Density (ASTM C188) (g/cm ³)	B	3.15

Additional Data

Type	Limestone	Inorganic Processing Addition
Amount	4.4	--
SiO ₂ (%)	7.0	--
Al ₂ O ₃ (%)	0.5	--
Fe ₂ O ₃ (%)	0.2	--
CaO (%)	50.5	--
SO ₃ (%)	0.4	--

This cement meets ASTM C150-18 and AASHTO M 85-18 Specification for Type I-II Portland Cement

This cement also meets all applicable FDOT (Facility ID: CMT 29), GADOT (Source Code: 53), ALDOT (CAMMS ID: 10146), SCDOT,

and NCDOT (Plant ID: CM69) specifications for Type I-II cement

*It is permissible to exceed the max value for SO₃ content, provided it is demonstrated by ASTM C1038 that the cement will not develop expansion exceeding 0.020% in 14 Days

** Maximum fineness limits do not apply if the sum of C₃S + 4.75C₃A is less than or equal to 90.

A Not applicable.

B Test result represents most recent value and is provided for information only.

March 16, 2020

Brandford Cement Plant

Suwannee American Cement

5117 U.S. Hwy 27

Brandford, FL 32008

Tel: (386) 935-5013 - Fax: (386) 935-5080

**Claudia Urrutia
Quality Manager**