



Suwannee American Cement Branford Plant

Portland Cement Type IL (10)

Silos: 4

Production Period : 2/1/2020 To 2/29/2020

STANDARD REQUIREMENTS

Chemical Data			Physical Data		
Item	Spec. Limit	Results	Item	Spec. Limit	Results
SiO ₂ (%)	A	19.3	Air Content of mortar (volume %)	12 max	6
Al ₂ O ₃ (%)	A	4.8	Blaine fineness (m ² /kg)**	A	450
Fe ₂ O ₃ (%)	A	3.1	Autoclave expansion (%)	-0.20 min/0.80 max	0.06
CaO (%)	A	64.0	Fineness, retained in #325	A	1.6
MgO (%)	A	0.6	Compressive strength (MPa/[psi]):		
SO ₃ (%)*	3.0 max	3.1	1 day		15.8 [2300]
Loss of ignition (%)	10.0 max	5.2	3 days	13.0[1890] min	28.2 [4090]
Na ₂ O (%)	A	0.14	7 days	20.0[2900] min	35.3 [5120]
K ₂ O (%)	A	0.21	28 days (previous month)	28.0[4060] min	44.0 [6380]
Insoluble residue (%)	A	0.59	Time of setting (minutes)		
CO ₂ (%)	A	3.6	(Vicat) Initial	45 min	109
Limestone (%)	15.0 max	9.4	(Vicat) Final	375 max	225
CaCO ₃ in limestone (%)	70 min	88	Sulfate Resistance (ASTM C1012 180d) (%)	0.10 max	0.05
Inorganic process addition (%)	5.0 max	--	Heat of hydration (ASTM C1702 3d)	B	271
Sum of C ₃ S + 4.75C ₃ A	A	90	Mortar Bar Expansion (ASTM C1038) (%)*	0.020 max	0.010
Potential phase composition			Base Cement Phase Composition		
C ₃ S (%)	A	54	C ₃ S (%)		60
C ₂ S (%)	A	13	C ₂ S (%)		14
C ₃ A (%)	A	7	C ₃ A (%)		8
C ₄ AF (%)	A	9	C ₄ AF (%)		10

OPTIONAL REQUIREMENTS

Item	Spec. Limit	Results	Item	Spec. Limit	Results
Equiv. Alkalies (%)	0.60 max	0.28	False Set (%)	50 min	90
Chloride (%)	B	0.01	Density (ASTM C188) (g/cm ³)	B	3.15

Additional Data

Type	Limestone	Inorganic Processing Addition
Amount	9.4	--
SiO ₂ (%)	7.0	--
Al ₂ O ₃ (%)	0.5	--
Fe ₂ O ₃ (%)	0.2	--
CaO (%)	50.5	--
SO ₃ (%)	0.4	--

This cement meets ASTM C595 and AASHTO M240 Specification for Type IL (MS) Portland Cement

This cement also meets all applicable FDOT (Facility ID: CMT 29), SCDOT, and NCDOT (Plant ID: CM69) specifications for Type IL cement

*It is permissible to exceed the max value for SO₃ content, provided it is demonstrated by ASTM C1038 that the cement will not develop expansion exceeding 0.020% in 14 Days

A Not applicable.

B Test result represents most recent value and is provided for information only.

C Test result is not yet available

March 16, 2020
 Brandford Cement Plant
 Suwannee American Cement
 5117 U.S. Hwy 27
 Brandford, FL 32008
 Tel: (386) 935-5013 - Fax: (386) 935-5080


Claudia Urrutia
 Quality Manager