



# Suwannee American Cement Branford Plant

**Portland Cement Type IL (10)**

**Silos: 2, 4**

Production Period : 7/1/2020 To 7/31/2020

## STANDARD REQUIREMENTS

Chemical Data			Physical Data		
Item	Spec. Limit	Results	Item	Spec. Limit	Results
SiO <sub>2</sub> (%)	A	19.1	Air Content of mortar (volume %)	12 max	6
Al <sub>2</sub> O <sub>3</sub> (%)	A	4.8	Blaine fineness (m <sup>2</sup> /kg)**	A	466
Fe <sub>2</sub> O <sub>3</sub> (%)	A	3.1	Autoclave expansion (%)	-0.20 min/0.80 max	0.03
CaO (%)	A	63.6	Fineness, retained in #325	A	2.1
MgO (%)	A	0.6	Compressive strength (MPa/[psi]):		
SO <sub>3</sub> (%)*	3.0 max	3.1	1 day		16.3 [2370]
Loss of ignition (%)	10.0 max	5.0	3 days	13.0[1890] min	27.6 [4010]
Na <sub>2</sub> O (%)	A	0.10	7 days	20.0[2900] min	36.1 [5230]
K <sub>2</sub> O (%)	A	0.14	28 days (previous month)	28.0[4060] min	44.0 [6380]
Insoluble residue (%)	A	0.26	Time of setting (minutes)		
CO <sub>2</sub> (%)	A	3.9	(Vicat) Initial	45 min	88
Limestone (%)	15.0 max	10.4	(Vicat) Final	375 max	225
CaCO <sub>3</sub> in limestone (%)	70 min	87	Sulfate Resistance (ASTM C1012 180d) (%)	0.10 max	0.05
Inorganic process addition (%)	5.0 max	--	Heat of hydration (ASTM C1702 3d)	B	288
Sum of C <sub>3</sub> S + 4.75C <sub>3</sub> A	A	87	Mortar Bar Expansion (ASTM C1038) (%)*	0.020 max	0.010
Potential phase composition			Base Cement Phase Composition		
C <sub>3</sub> S (%)	A	53	C <sub>3</sub> S (%)		59
C <sub>2</sub> S (%)	A	13	C <sub>2</sub> S (%)		15
C <sub>3</sub> A (%)	A	7	C <sub>3</sub> A (%)		8
C <sub>4</sub> AF (%)	A	9	C <sub>4</sub> AF (%)		11

## OPTIONAL REQUIREMENTS

Item	Spec. Limit	Results	Item	Spec. Limit	Results
Equiv. Alkalies (%)	0.60 max	0.19	False Set (%)	50 min	82
Chloride (%)	B	0.01	Density (ASTM C188) (g/cm <sup>3</sup> )	B	3.15

### Additional Data

Type	Limestone	Inorganic Processing Addition
Amount	10.4	--
SiO <sub>2</sub> (%)	6.7	--
Al <sub>2</sub> O <sub>3</sub> (%)	0.8	--
Fe <sub>2</sub> O <sub>3</sub> (%)	0.2	--
CaO (%)	51.0	--
SO <sub>3</sub> (%)	0.4	--

*This cement meets ASTM C595 and AASHTO M240 Specification for Type IL (MS) Portland Cement*

*This cement also meets all applicable FDOT (Facility ID: CMT 29), SCDOT, and NCDOT (Plant ID: CM69) specifications for Type IL cement*

\*It is permissible to exceed the max value for SO<sub>3</sub> content, provided it is demonstrated by ASTM C1038 that the cement will not develop expansion exceeding 0.020% in 14 Days

A Not applicable.

B Test result represents most recent value and is provided for information only.

C Test result is not yet available

August 16, 2020  
 Brandford Cement Plant  
 Suwannee American Cement  
 5117 U.S. Hwy 27  
 Brandford, FL 32008  
 Tel: (386) 935-5013 - Fax: (386) 935-5080

  
**Claudia Urrutia**  
 Quality Manager